

Simply Bearings Ltd

Authorised Precision Ball and Roller Distributors in the UK

316 Stainless Steel Data Sheet

Properties:

Hardness	25 - 39 HRC	140-160 HB
Density	0.290 lbs/in ³	
Tensile Strength	180,000 psi	
Yield Strength	150,000 psi	

Chemical Make Up %:

Carbon C	0.08 % Max
Chromium Cr	16 - 18 %
Nickel Ni	10 - 14 %
Silicon Si	1.0 % Max
Molybdenum Mo	2 - 3 % Max
Manganese Mn	2.0 % Max
Phosphor P	0.045 % Max
Sulphur S	0.03 % Max

Specification:

Specification	Equivalent Standards
AISI 316	AFN Z6CND17-11
	DIN X5 Cr Ni Mo 17122
	JIS SUS 316
	Wks 1.4401

Synopsis:

Un-hardened austenitic stainless steel with good corrosion resistance to sea water, dilute nitric, sulphuric and acetic acids, photo chemicals, inks, bleaches, dyes etc. Is drillable / can be machined.

Typical Uses:

Marine and chemical process plant, cutlery and food use.

Attracted to Magnets: No but may show response to magnets after cold working

Available Grades: 50, 100, 500 & 1000

Simply Bearings Ltd ~ Halton House, Greenfold Way, Leigh, Lancashire, WN7-3XJ
Tel 01942 269 837 Fax 01942 605 420

Whilst every effort has been made to ensure the accuracy of the information we have supplied in this document we accept no liability should there be any errors.